



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: H01L 51/20	A1	(11) International Publication Number: WO 00/35028 (43) International Publication Date: 15 June 2000 (15.06.2000)
(21) International Application Number: PCT/GB99/04050 (22) International Filing Date: 07 December 1999 (07.12.1999) (30) Priority Data: 9827014.3 08 December 1998 (08.12.1998) GB 9901334.4 21 January 1999 (21.01.1999) GB (60) Parent Application or Grant CAMBRIDGE DISPLAY TECHNOLOGY LTD. [/]; (). BERGER, Paul [/]; (). BURROUGHES, Jeremy, Henley [/]; (). CARTER, Julian, Charles [/]; (). HEEKS, Stephen, Karl [/]; (). BERGER, Paul [/]; (). BURROUGHES, Jeremy, Henley [/]; (). CARTER, Julian, Charles [/]; (). HEEKS, Stephen, Karl [/]; (). HARTWELL, Ian, Peter ; ().		Published
(54) Title: DISPLAY DEVICES (54) Titre: DISPOSITIFS D'AFFICHAGE (57) Abstract A light-emissive device comprising: a light-emissive region (12); a first electrode (10) located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and a second electrode (11) located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type; and wherein there is a reflectivity-influencing structure (13) located on the non-viewing side of the light-emissive region and including a light absorbent layer comprising graphite and/or a fluoride or oxide of a low work function metal. (57) Abrégé L'invention concerne un dispositif électroluminescent comprenant une région électroluminescente (12) ; une première électrode (10) située sur le côté de visualisation de la région électroluminescente et injectant des porteurs de charge d'un premier type ; et une seconde électrode (11), située sur un côté de non visualisation de la région électroluminescente et injectant des porteurs de charge d'un second type. Le dispositif comporte également une structure (13) affectant le pouvoir de réflexion située sur le côté de non visualisation de la région électroluminescente, ainsi qu'une couche absorbant la lumière contenant du graphite et/ou un fluorure ou un oxyde d'un métal à faible énergie d'extraction.		

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : H01L 51/20		A1	(11) International Publication Number: WO 00/35028
			(43) International Publication Date: 15 June 2000 (15.06.00)
(21) International Application Number: PCT/GB99/04050		(74) Agents: HARTWELL, Ian, Peter, Cambridge Display Technology Ltd., Greenwich House, Madingley Rise, Madingley Road, Cambridge CB3 0HJ (GB) et al.	
(22) International Filing Date: 7 December 1999 (07.12.99)			
(30) Priority Data: 9827014.3 8 December 1998 (08.12.98) GB 9901334.4 21 January 1999 (21.01.99) GB		(81) Designated States: AT, AU, BR, CA, CH, CN, CZ, DE, DK, ES, FI, GB, IL, IN, JP, KR, LU, MX, PT, RU, SE, SG, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(71) Applicant (for all designated States except US): CAMBRIDGE DISPLAY TECHNOLOGY LTD. [GB/GB]; Greenwich House, Madingley Rise, Madingley Road, Cambridge CB3 0HJ (GB).		Published With international search report.	
(72) Inventors; and (75) Inventors/Applicants (for US only): BERGER, Paul [US/US]; 17 West Ridge Court, Newark, DE 19711 (US). BURROUGHS, Jeremy, Henley [GB/GB]; Cambridge Display Technology Ltd., Greenwich House, Madingley Rise, Madingley Road, Cambridge CB3 0HJ (GB). CARTER, Julian, Charles [GB/GB]; Cambridge Display Technology Ltd., Greenwich House, Madingley Rise, Madingley Road, Cambridge CB3 0HJ (GB). HEEKS, Stephen, Karl [GB/GB]; Cambridge Display Technology Ltd., Greenwich House, Madingley Rise, Madingley Road, Cambridge CB3 0HJ (GB).			
(54) Title: DISPLAY DEVICES			
(57) Abstract			
<p>A light-emissive device comprising: a light-emissive region (12); a first electrode (10) located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and a second electrode (11) located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type; and wherein there is a reflectivity-influencing structure (13) located on the non-viewing side of the light-emissive region and including a light absorbent layer comprising graphite and/or a fluoride or oxide of a low work function metal.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TC	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Description

5

10

15

20

25

30

35

40

45

50

55

5

DISPLAY DEVICES

10

This invention relates to display devices.

15

20

25

30

35

40

One specific class of display devices is those that use an organic material for light emission. Light-emissive organic materials are described in PCT/WO90/13148 and US 4,539,507, the contents of both of which are incorporated herein by reference. The basic structure of these devices is a light-emissive organic layer, for instance a film of a poly(p-phenylenevinylene ("PPV"), sandwiched between two electrodes. One of the electrodes (the cathode) injects negative charge carriers (electrons) and the other electrode (the anode) injects positive charge carriers (holes). The electrons and holes combine in the organic layer generating photons. In PCT/WO90/13148 the organic light-emissive material is a polymer. In US 4,539,507 the organic light-emissive material is of the class known as small molecule materials, such as (8-hydroxyquinoline)aluminium ("Alq3"). In a practical device one of the electrodes is typically transparent, to allow the photons to escape the device.

Figure 1 shows the typical cross-sectional structure of an organic light-emissive device ("OLED"). The OLED is typically fabricated on a glass or plastic substrate 1 coated with a transparent first electrode 2 such as indium-tin-oxide ("ITO"). Such coated substrates are commercially available. This ITO-coated substrate is covered with at least a layer of a thin film of an electroluminescent organic material 3 and a final layer forming a second electrode 4, which is typically a metal or alloy. Other layers can be added to the device, for example to improve charge transport between the electrodes and the electroluminescent material.

45

50

If light that is incident on the display can be reflected back towards a viewer, especially from the region of pixels that are intended to appear dark, then the apparent contrast between the pixels of the display can be reduced. This reduces the effectiveness of the display.

55

5

10

Many display devices are used in applications where power consumption is a crucial consideration - examples are battery-powered devices such as portable computers and mobile phones. There is therefore a drive to improve the efficiency of display devices.

15

20

According to one aspect of the present invention there is provided a light-emissive device comprising: a light-emissive region; a first electrode located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and a second electrode located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type; and wherein there is a reflectivity-influencing structure located on the non-viewing side of the light-emissive region and including a light absorbent layer comprising graphite and/or a fluoride or oxide of a low work function metal.

25

30

35

40

According to a second aspect of the present invention there is provided a light-emissive device comprising: a light-emissive region; a first electrode located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and a second electrode located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type; and wherein there is a reflectivity-influencing structure located on the non-viewing side of the light-emissive region and including a light-reflective layer and a light-transmissive spacing layer between the second electrode and the light-reflective layer, the thickness of the spacing layer being such as to space a reflective plane of the light-reflective layer by approximately half the wavelength of the optical mode of the device from at least part of the light-emissive region.

45

The first electrode is preferably at least partially light-transmissive, most preferably substantially transparent, at least to light of some or all of the wavelengths that can be emitted from the device. The first electrode could, for example, be formed of ITO (indium-tin oxide), TO (tin oxide) or gold. The first electrode is preferably disposed in a viewing direction from the light-emissive

50

55

5 region - that is between the light-emissive region and an expected location of a viewer. The first electrode may be in the form of a layer. Where the device includes more than one pixel more than one first electrode could be provided to
10 allow (in co-operation with the second electrode) each pixel to be individually addressed.

15 The second electrode may be at least partially light-transmissive, suitably substantially transparent, at least to light of some or all of the wavelengths that can be emitted from the device. This could be achieved by forming the second electrode from a light-transmissive material and/or by the second electrode being
20 relatively thin, for example less than 2, 5, 10, 20 or 30nm in thickness. Suitable materials for the second electrode include lithium, calcium and ITO. Alternatively, the second electrode could be reflective or non-reflective/light absorbent. In that case, the second electrode preferably itself provides the reflectivity-influencing
25 structure. Where the second electrode is light-absorbent it could be formed of a light-absorbent materials such as a fluoride or oxides of a low work function metal such as Li, Ca, Mg, Cs, Ba, Yb, Sm etc. (together, optionally, with a conductive material such as Al, which could be co-deposited with the oxide or fluoride), or of
30 a low work function metal incorporating and preferably co-deposited with a light-absorbent material such as carbon (graphite). The said low work function metal may have a work function below 4.0eV. The said low work function metal may have a work function below 3.5eV. The said low work function metal may have a
35 work function below 3.2eV. The said low work function metal may have a work function below 3.0eV. A suitable range of thickness for the second electrode is in the range from 50 to 1000nm, preferably from 100 to 300 nm.

40 The first electrode and/or the second electrode preferably comprise electrically conductive material, for example metallic material. One of the electrodes (the hole-injecting electrode) preferably has a work function of greater than 4.3 eV. That layer may comprise a metallic oxide such as indium-tin oxide ("ITO") or tin
45 oxide ("TO") or a high work function metal such as Au or Pt. This may be the first electrode or the second electrode. The other electrode (the electron-injecting

50

55

5 electrode) preferably has a work function less than 3.5 eV. That layer may
suitably be made of a metal with a low work function (Ca, Ba, Yb, Sm, Li etc.) or
10 an alloy or multi-layer structure comprising one or more of such metals together
optionally with other metals (e.g. Al). This may be the second electrode or the
first electrode. The rear electrode is preferably at least partially light-absorbent.
This may be achieved by incorporating a layer of light-absorbent material such as
15 carbon in the electrode. Such material is preferably also electrically conductive.

The reflectivity-influencing structure could be located adjacent the second
20 electrode. The reflectivity-influencing structure then suitably influences the
reflectivity of the rear (non-viewing side) of the device, being (for example)
substantially light-absorbent or substantially light-reflective. The reflectivity-
influencing structure may include distinct substantially light-absorbent and
substantially light-reflective areas.

25 In the first aspect of the invention the reflectivity-influencing structure may
comprise a light-absorbent layer. Such a layer is suitably for reducing reflection
by or through the second electrode of light emitted from the light-emissive region
30 and/or absorbing light that has been transmitted through the second electrode
and/or absorbing light that is incident on the device from another source. Such a
light-absorbent layer is preferably located adjacent to the second electrode;
alternatively the light-absorbent layer could be spaced from the second electrode,
35 for example by an insulating material. The presence of the reflectivity-influencing
structure adjacent or more generally behind the second electrode suitably renders
the second electrode substantially non-reflective to light emitted from the light-
emissive region. Such a light-absorbent layer is preferably formed from a light-
40 absorbent material - for example the light-absorbent layer of the reflectivity-
influencing structure could comprise graphite. Where the device comprises a
plurality of individual pixels the light-absorbent layer is preferably common to a
45 plurality of pixels.

5 In the second aspect of the invention the reflectivity-influencing structure may
comprise a light-reflective layer. Such a layer is suitably for influencing the
10 coincidence within the device of the optical field (e.g. an anti-node of the optical
field) and a part of the light-emissive region. Such a part of the light-emissive
region is suitably a region at which there is some or significant electron/hole
15 recombination (preferably to generate photons). The said part is preferably a
principal recombination site or plane of the light-emissive layer. The said part is
most preferably the peak recombination site or plane of the device. The
reflectivity-influencing structure preferably comprises a light-transmissive spacing
20 layer between the second electrode and such a light-reflective layer, suitably for
spacing the light-reflective layer from the light-emissive layer and preferably by a
predetermined spacing. The spacing layer could be provided by material integral
with the second electrode itself - for example by virtue of the thickness of the
25 second electrode. The thickness of the spacer is preferably such as to space a
reflector of the reflection-influencing structure from at least part of the light-
emissive region by approximately half the wavelength of the optical mode of the
device. That reflector may be one of the major surfaces of the reflective layer
(those closer to and further from the light-emissive layer) or may be a reflective
30 structure (such as a distributed Bragg reflector) defined by the reflective layer.
The thickness of the spacer is most preferably such as to space the reflector by
approximately or substantially half the wavelength of the optical mode of the
device from the region of the light-emissive region at which the optical field is
35 approximately or substantially at its peak.

40 The light-absorbent or light-reflecting layers mentioned above of the reflection-
influencing structure are preferably in optical communication with the light-
emissive layer of the device so that light from the light-emissive layer may reach
the light-absorbent or light-reflecting layers.

45 The reflection-influencing structure is preferably electrically conductive, suitably to
permit electrical contact to be made to the second electrode through the reflection
influencing structure.

According to a third aspect of the present invention there is provided a light-emissive device comprising: a light-emissive region; a first electrode located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and a second electrode located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type; and a contrast enhancing structure located on the non-viewing side of the light-emissive region and including a reflective structure having different reflectivity for different wavelengths of incident light, and having a reflectivity peak encompassing an emission wavelength of the light-emissive region. In this aspect of the invention the reflective structure is suitably a distributed Bragg reflector. In this aspect of the invention the second electrode suitably comprises a layer located on the non-viewing side of the reflective structure and a plurality of through paths passing through the reflective structure for electrical conduction between the said layer of the second electrode and the light-emissive region. The through paths preferably occupy less than 15% or less than 10% of the emissive area of the device. The through paths may occupy between 15% and 5% of the emissive area of the device. In this aspect of the invention the cathode may comprise a transparent layer located between the reflective structure and the light-emissive region. That transparent layer may be in contact with the through paths.

In general, the light-emissive material is suitably an organic material and preferably a polymer material. The light-emissive material is preferably a semiconductive and/or conjugated polymer material. Alternatively the light-emissive material could be of other types, for example sublimed small molecule films or inorganic light-emissive material. The or each organic light-emissive material may comprise one or more individual organic materials, suitably polymers, preferably fully or partially conjugated polymers. Example materials include one or more of the following in any combination: poly(p-phenylenevinylene) ("PPV"), poly(2-methoxy-5(2'-ethyl)hexyloxyphenylenevinylene) ("MEH-PPV"), one or more PPV-derivatives (e.g. di-alkoxy or di-alkyl derivatives), polyfluorenes and/or co-polymers incorporating polyfluorene

5 segments, PPVs and related co-polymers, poly(2,7-(9,9-di-n-octylfluorene)-(1,4-phenylene-((4-secbutylphenyl)imino)-1,4-phenylene)) ("TFB"), poly(2,7-(9,9-di-n-octylfluorene) - (1,4-phenylene-((4-methylphenyl)imino)-1,4-phenylene-((4 -
10 methylphenyl)imino) - 1,4-phenylene)) ("PFM"), poly(2,7 - (9,9 - di-n-octylfluorene) - (1,4-phenylene-((4-methoxyphenyl)imino)-1,4-phenylene- ((4-methoxyphenyl)imino)-1,4-phenylene)) ("PFMO"), poly (2,7-(9,9-di-n-octylfluorene) ("F8") or (2,7-(9,9-di-n-octylfluorene)-3,6-Benzothiadiazole) ("F8BT"). Alternative materials include small molecule materials such as Alq3.

20 One or more charge-transport layers may be provided between the light-emissive region and one or both of the electrodes. The or each charge transport layer may suitably comprise one or more polymers such as polystyrene sulphonic acid doped polyethylene dioxythiophene ("PEDOT-PSS"), poly(2,7-(9,9-di-n-octylfluorene)-(1,4-phenylene-(4-imino(benzoic acid))-1,4-phenylene-(4-
25 imino(benzoic acid))-1,4-phenylene)) ("BFA"), polyaniline and PPV.

30 Any implied physical orientation of the device is not necessarily related to its physical orientation during use or manufacture.

The present invention will now be described by way of example with reference to the accompanying drawings, in which:

35 figure 2 is a cross-section of a first device;

figure 3 is a plan view of a second device;

figure 4 is a cross-section of the device of figure 3 on the line A-A'; and

figure 5 is a cross-section of a third device;

40 figure 6 is a plan view of a fourth device;

figure 7 is a cross-section of the fourth device; and

figure 8 shows the reflectivity of a DBR against wavelength.

The figures are not to scale.

45 The device of figure 2 comprises an anode electrode layer 10, and a cathode electrode 11. Located between the electrode layers is a layer 12 of light-emissive

material. The anode electrode is formed of transparent ITO. The cathode electrode is formed of calcium. The cathode is sufficiently thin that it is not significantly reflective. Behind the cathode is a layer 13 of carbon. When a suitable voltage is applied across the electrodes light is emitted from the light-emissive material substantially omnidirectionally. Some of the light is emitted forwards towards the anode and passes directly out of the device through the anode. Some of the light is emitted backwards towards the cathode. Incident light that shines on to the display from an external source can be absorbed by the carbon layer 13. Because this light is absorbed it does not reflect back towards a viewer - this can improve the effect produced by the display, as described in detail below.

The device of figure 2 may be formed starting with a commercially-available glass sheet coated with ITO. The glass sheet (14 in figure 2) forms the substrate for subsequent deposition steps. The glass sheet could be a sheet of sodalime or borosilicate glass of a thickness of, for instance, 1mm. Instead of glass other materials such as Perspex could be used. The thickness of the ITO coating is suitably around 100 to 150nm and the ITO suitably has a sheet resistance of between 10 and 30 Ω/\square . Over the ITO anode is deposited a hole transport or injecting layer 15. The hole transport layer is formed from a solution containing PEDOT:PSS with a ratio of PEDOT to PSS of around 1 to 5. The thickness of the hole transport layer is suitably around 50nm. The hole transport layer is spin-coated from solution and then baked typically at 200°C for 1 hour in a nitrogen environment. Then an electroluminescent layer 12 comprising 20% TFB in 5BTF8 is coated over the hole transport layer by spin-coating typically to a thickness of 90nm. The term 5BTF8 refers to poly (2,7-(9,9-di-*n*-octylfluorene) ("F8") doped with 5% poly-(2,7-(9,9-di-*n*-octylfluorene)-3,6-benzothiadiazole) ("F8BT"). Then a transparent or semitransparent layer of a low work function material such as calcium is thermally evaporated on to the electroluminescent layer in vacuo at a base pressure of less than 10^{-8} mbar to form the cathode layer 11. The thickness of this layer is preferably greater than around 1nm but less than the thickness at which the calcium layer would be non-transparent - typically around 20nm. Over

5 this layer is deposited by electron beam evaporation a layer 13 of carbon with a
thickness of between 100 and 500nm at base pressures less than 10^{-8} mbar. On
10 this layer is deposited by sputter deposition a layer 16 of aluminium with a
thickness of between 100 and 1000nm at base pressures less than 10^{-8} mbar. In
this embodiment the low work function layer 11 is chosen to act as an efficient
15 electron injector for injecting electrons into the light-emissive region. The carbon
layer 13 acts as a light-absorbing layer yet has a conductivity that is low enough
not to significantly increase the drive voltage of the device. The sputtered
aluminium layer 16 acts as an encapsulant, having a compact morphology with
20 low pinhole density and small grain size. Contacts can be attached to the device
(between layers 16 and 10) and it can finally be sealed in epoxy resin for
environmental protection.

25 Figures 3 and 4 show a multi-pixel display device that makes use of the principle
described above in connection with the device of figure 2. The device of figures 3
and 4 comprises a set of parallel anode electrode strips 20 in a common anode
plane and a set of parallel cathode electrode strips 21 in a common cathode plane
30 spaced from the anode plane. Between the anode and cathode electrodes is a
light-emissive layer 22. The areas where anode and cathode electrode strips
overlap define pixels of the display device. By using a passive matrix addressing
scheme individual pixels can be caused to emit light. (The device could
35 alternatively be configured to allow active matrix or other addressing schemes to
be used). Figure 4 shows that each cathode electrode comprises three layers: an
injection layer 75 of a low work function material such as calcium adjacent to the
emissive layer 22, an intermediate layer 76 of a light-absorbent material such as
40 carbon (graphite) and a conduction layer 77 of a highly conductive material such
as aluminium. Together these make up a cathode plane 81. In general, the
injection layer is suitably of a material that has good properties of injection into the
light-emissive layer 22; the intermediate layer is suitably of a material that has
45 good light-absorbency properties and the conduction layer is of a highly
conductive material. The conduction layer may be significantly thicker than the
other layers and preferably helps to distribute charge evenly along the electrode

5 structure. Where the material chosen for one of the layers can also perform the
function of another layer then that other layer could be omitted. For instance, if
10 the selected light emissive material were one into which good charge injection
could be achieved from carbon then the layer 75 could be omitted, and/or if the
layers 75 and/or 76 provided adequate conduction then the layer 77 could be
omitted. The light absorbent layer 76 preferably lies between the other two layers
15 (where present), in which case it should be electrically conductive, but it could lie
behind the other two layers. Alternatively, or in addition, a light absorbent layer
covering the whole structure could be provided (layer 29 in figure 4). If that layer
were of a conductive material such as carbon then an insulating layer 23 could be
20 provided to prevent shorting between the cathode strips 21.

The effect of the light-absorbent layer 76 is to absorb light that is incident on the
25 display and could otherwise be reflected from the display causing a reduction in
contrast. This is illustrated by light rays 80 in figure 4, which are absorbed by
layers 23 and 29. The light-absorbent layer therefore helps to increase contrast.
The light-absorbent layer may also help to reduce transmission within the device
30 itself of light emitted from the light-emissive layer 22. This can help to increase
contrast by avoiding such light emerging from the device at a location where it
appears to come from a different pixel from the one from which it was emitted.

35 One of the contacts from the display driver is applied to the layer 77.

A carbon layer or other non-reflective layer could also be provided in front of the
40 light-emissive layer 22 in the lateral spaces between the pixels to further reduce
reflection of ambient light.

The principles described above in relation to the devices of figures 2 to 4 can
45 therefore improve contrast between adjacent pixels of a device and improve the
pattern of light emission from a single pixel by reducing emission of more
obliquely angled light and reducing reflection of ambient light.

5

10

15

20

25

30

35

40

45

50

Figure 5 shows another display device. The device of figure 5 comprises an anode electrode layer 40, and a cathode electrode 41. Located between the electrode layers is a layer 42 of light-emissive material. The anode electrode and the cathode electrode are formed of transparent ITO. Alternatively, for example, the electrodes could be formed from a thin layer of a low work function metal such as calcium adjacent to an transparent spacing layer formed from a material such as ITO, ZnSe, ZnS etc.). When a suitable voltage is applied across the electrodes light is emitted from the light-emissive material substantially omnidirectionally. Some of the light is emitted forwards towards the anode and passes directly out of the device through the anode. Some of the light is emitted backwards towards the cathode, through which it passes into a reflection structure indicated generally at 43. The reflection structure comprises a reflective layer 44 and a transparent spacing layer 46. The spacing layer lies between the cathode 41 and the reflective layer 44 and spaces the reflective layer from the light-emissive region 42. The reflective layer reflects backwardly emitted light forwards so that it can pass back through the cathode electrode 41, the light-emissive layer 42 the anode electrode 40 and the glass substrate 47 and out of the device (see ray 48).

In figure 5 curve 49 illustrates the form of the optical field and region 50 illustrates the zone in the device at which electron/hole recombination to generate photons is most intense. The equivalent features are illustrated at 60 and 61 respectively for the device of figure 1. The thickness of the spacing layer in the device of figure 5 is ideally chosen so that the plane (or one of the planes) of the reflective layer 44 that acts to return backwardly emitted light is spaced from the emissive layer by a distance such that at at least one emission frequency of the device the peak of the optical mode of the whole reflective arrangement (see curve 49) coincides with the region of peak electron/hole recombination in the light-emissive layer of the device. The effect of this is to arrange that the area of light generation in the device is at a more efficient plane of the device of figure 5 than in the device of figure 1, by tuning the peak of the optical field (anti-node) to coincide with the hole/electron recombination zone of the emissive layer. This optimises (or at least partially optimises) the location for efficient light generation for a given

5 wavelength. The wavelength for which the device is optimised preferably is or is
near the peak intensity emission wavelength. This ideal arrangement calls for
10 very precise spacing of the respective layers; however, considerable benefits can
be gained by arranging the layers approximately or substantially in that way.

15 The device of figure 5 may be formed by a similar route to that described above
for the device of figure 2 up to the formation of the cathode electrode. Then for
the device of figure 5 the spacing layer 46 is formed by depositing ITO, ZnSe, ZnS
or the like to the required thickness, preferably on top of a thin layer of a low work-
20 function metal such as calcium. Over the ITO spacing layer the reflective layer 44
is formed from reflective material such as aluminium. In an alternative
embodiment a conducting dielectric stack next to or spaced from the cathode
could be used as the reflector. Such a stack could be formed, for example, of
alternating layers of ITO and NiO.

25 In another alternative embodiment, one of the electrodes could be formed of a
reflectivity influencing material. The anode or the cathode could be reflective or
non-reflective (light-absorbent). This could be achieved by choosing a material
30 with the desired reflectivity properties and the preferred charge conduction and
injection properties. An electrically suitable material could be treated (e.g. by
surface treatment or incorporation into it of a reflectivity influencing additive) to
obtain the desired reflectivity properties.

35 One specific example is for the rear electrode (the one furthest from a viewer) to
be non-reflective. In a device arranged generally as those in figures 1 to 5, this
calls for a non-reflective cathode. (In other devices the anode may be the rear
40 electrode). One suitable material for a reflective or non-reflective cathode is
LiF:Al. When the Al component of a LiF:Al film is greater than 50% the LiF:Al
films are reflective. When the Al component is between 50% and 30% the films
are non-reflective. When the Al component is <30% the films are semi-
45 transparent but also have very high resistivities. Therefore, in the range 50:50 to
70:30 LiF:Al LiF/Al films are useful for making a black (non-reflective) cathode.

5

10

15

20

An example device having a non-reflective rear electrode (in this case the cathode) can be manufactured as follows. On to a glass substrate a 150nm thick layer of ITO is deposited to act as an anode electrode. Then a 50nm thick layer of PEDOT/PSS is deposited to act as a hole transport layer. Over that an 80nm thick layer of a polyfluorene based electroluminescent polymer is formed. Finally the non-reflective cathode layer is deposited as a 200nm thick layer of co-evaporated LiF and Al, with the LiF:Al evaporation rates being 60:40. On top of this layer a 400nm thick Al layer is deposited. In varying this specific design of device it should be noted that the range of potential thickness for the LiF:Al layer depends on the composition since the greater the proportion of LiF in the layer the more transparent the layer becomes. For layers of composition 60:40 LiF:Al 200nm is just thick enough. A suitable range of thickness is from 50 to 1000nm.

25

30

35

40

Alternative non-reflective cathode materials include generally fluorides and oxides of low work function metals such as Li, Ca, Mg, Cs, preferably together with an inherently highly conductive metal such as Al or Cu (although in some situations Cu may be less preferred because of its tendency to quench polymers' electroluminescence). Specific examples include CsF, MgF, CaF, LiO, CaO, which could be co-evaporated with Al or sputtered from a composite target including Al. The required ratios of the conductor (Al) with the insulating fluorides and oxides can easily be determined by experimentation in each case but might be expected to be similar to those discussed for the LiF:Al system above. Another alternative route to a low reflectivity or non-reflective or cathode is to co-evaporate or sputter a low work function material with carbon. Examples include the low work function metals Ca, Li etc and also the fluorides and oxides listed above.

45

50

Figure 6 is a plan view and figure 7 a cross-sectional view of another alternative device. The device comprises an anode electrode 60, a hole transport layer 62, a cathode electrode 63, a light-emissive layer 64 and a distributed Bragg reflector (DBR) layer 65. The DBR is located on the non-viewing side of the light-emissive

55

5 layer. The bulk (66) of the cathode 63 is located on the non-viewing side of the
DBR. To allow charge to pass from the bulk of the cathode to the light-emissive
10 region cathode vias 67 are provided through the DBR. The vias occupy a
relatively small proportion of the area of the device: for example around 15% to
5%. To even out charge injection into the emissive layer a further layer 68 of the
15 cathode which is sufficiently thin to be transparent is provided between the DBR
and the light-emitting region. If the DBR were conductive, or the vias were
closely spaced, or uniformity could otherwise be achieved then the layer 68 could
be omitted. The mesh-like arrangement of vias (see figure 6) could be formed by
means of deposition through a shadow mask.

20 A DBR comprises of a stack of regularly alternating higher- and lower-refractive
index dielectrics (light transmissive materials) fabricated to fulfil the Bragg
condition for reflection at particular wavelengths. This occurs when the optical
25 path of the periodicity in the dielectric stack corresponds to half a wavelength, and
the reflectivity is further optimised when the DBR stack obeys the following
equation:

$$\frac{1}{2} \lambda = n_1 d_1 + n_2 d_2,$$

30 where n_1 , n_2 are the respective refractive indices; d_1 , d_2 are the corresponding
component film thicknesses in the DBR; and λ is the desired reflection
wavelength. Figure 8 shows the reflectivity of a DBR against wavelength, the
reflectivity peaking at that optimum and being much lower for other wavelengths.

35 In the device of figures 6 and 7 the DBR is arranged so that the emission
wavelength of the light-emissive layer (or its principal emission wavelength) lies
40 within the reflectivity peak of the DBR, and most preferably at or near the
maximum reflectivity of the DBR. The effect of this is that the DBR can act to
increase the contrast of the device without significantly reducing its efficiency.
Light emitted rearwards from the light-emissive layer is reflected efficiently (e.g.
45 with around 95% to 100% reflectivity) back towards a viewer by the DBR. Incident
light that is not at or near the emission wavelength of the light-emitting layer, and
therefore not within the reflectivity peak of the DBR, is reflected much less (e.g.

only 5% to 10%) and tends to be absorbed by the DBR, improving the contrast of the device. The peaky reflectivity of the DBR may also serve to enhance colour purity of the emission from the device.

The vias may be reflective to a range of wavelengths, so it is preferred to minimise the area occupied by the vias, for example to below 15% and preferably below 10%.

Some variations on the devices described above will now be described. In any of the devices one or more charge transport layers (e.g. layers 15, 70, 71) may be formed between the light-emissive layer and either or both of the electrodes to assist charge transport between the respective electrode and the light-emissive layer and/or to resist charge transport in the opposite direction. The principles described above could be applied to other types of organic or inorganic display devices. One specific alternative example is the class of display devices that use sublimed molecular films for light emission, as described for example in "Organic Electroluminescent Diodes", C. W. Tang and S. A. VanSlyke, Appl. Phys. Lett. 51, 913-915 (1987). The locations of the electrodes could be reversed so that the cathode is located at the front of the display (closest to the viewer) and the anode is at the back. Other materials or classes of materials could be used instead of those mentioned above, although this may impair performance of the devices.

The applicant draws attention to the fact that the present invention may include any feature or combination of features disclosed herein either implicitly or explicitly or any generalisation thereof, without limitation to the scope of any of the present claims. In view of the foregoing description it will be evident to a person skilled in the art that various modifications may be made within the scope of the invention.

Claims

5

10

15

20

25

30

35

40

45

50

55

CLAIMS

1. A light-emissive device comprising:

a light-emissive region;

a first electrode located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and

a second electrode located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type;

and wherein there is a reflectivity-influencing structure located on the non-viewing side of the light-emissive region and including a light absorbent layer comprising graphite and/or a fluoride or oxide of a low work function metal.

2. A light-emissive device as claimed in claim 1, wherein the first electrode is at least partially light-transmissive.

3. A light-emissive device as claimed in claim 1 or 2, wherein the reflectivity influencing structure is located on the opposite side of the second electrode from the light-emissive region.

4. A light-emissive device as claimed in claim 3, wherein the second electrode is at least partially light-transmissive.

5. A light-emissive device as claimed in claim 3 or 4, wherein the thickness of the second electrode is less than 30nm.

6. A light-emissive device as claimed in any of claims 3 to 5, wherein the reflectivity-influencing structure is adjacent the second electrode.

7. A light-emissive device as claimed in claim 1 or 2, wherein the second electrode provides the reflectivity-influencing structure.

5

8. A light-emissive device as claimed in claim 7, wherein the second electrode comprises a fluoride or oxide of a low work function metal.

10

9. A light-emissive device as claimed in claim 8, wherein the second electrode comprises aluminium.

15

10. A light-emissive device as claimed in any preceding claim, wherein the reflectivity-influencing structure is effective to absorb light emitted from the light-emissive region that reaches it through the second electrode and/or incident light.

20

11. A light-emissive device as claimed in any of claims 7 to 10 as dependant directly or indirectly on claim 6, wherein the presence of the reflectivity-influencing structure adjacent the second electrode renders the second electrode substantially non-reflective to light emitted from the light-emissive region and/or incident light.

25

12. A light-emissive device as claimed in any preceding claim, wherein the second electrode comprises an electrically conductive material.

30

13. A light-emissive device as claimed in any preceding claim, wherein the light-emissive layer comprises an organic light-emissive material.

35

14. A light-emissive device as claimed in any preceding claim, wherein the light-emissive layer comprises a polymer light-emissive material.

40

15. A light-emissive device as claimed in any preceding claim, wherein the light-emissive layer comprises a conjugated polymer material.

45

16. A light-emissive device as claimed in any preceding claim, wherein the reflection-influencing layer is electrically conductive.

17. A light-emissive device comprising:

50

55

5

a light-emissive region;

a first electrode located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and

10

a second electrode located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type;

15

and wherein there is a reflectivity-influencing structure located on the non-viewing side of the light-emissive region and including a light-reflective layer and a light-transmissive spacing layer between the second electrode and the light-reflective layer, the thickness of the spacing layer being such as to space a reflective plane of the light-reflective layer by approximately half the wavelength of the optical mode of the device from at least part of the light-emissive region.

20

25

18. A light-emissive device as claimed in claim 17, wherein the said part of the light-emissive region is a part at which, when the device is in operation, there is significant electron/hole recombination.

30

19. A light-emissive device as claimed in claim 18, wherein the said part of the light-emissive region is a principal region for electron/hole recombination.

35

20. A light-emissive device as claimed in any of claims 17 to 19, wherein the said plane of the light-reflective layer is the major surface of the light-reflective layer that is closer to the light-emissive region.

40

21. A light-emissive device as claimed in any of claims 17 to 20, wherein the second electrode comprises an electrically conductive material.

45

22. A light-emissive device as claimed in any of claims 17 to 21, wherein the light-emissive layer comprises an organic light-emissive material.

50

23. A light-emissive device as claimed in any of claims 17 to 22, wherein the light-emissive layer comprises a polymer light-emissive material.

55

5

24. A light-emissive device as claimed in any of claims 17 to 23, wherein the light-emissive layer comprises a conjugated polymer material.

10

25. A light-emissive device as claimed in any of claims 17 to 24, wherein the reflection-influencing layer is electrically conductive.

15

26. A light-emissive device comprising:

a light-emissive region;

a first electrode located on a viewing side of the light-emissive region for injecting charge carriers of a first type; and

20

a second electrode located on a non-viewing side of the light-emissive region for injecting charge carriers of a second type;

25

and a contrast enhancing structure located on the non-viewing side of the light-emissive region and including a reflective structure having different reflectivity for different wavelengths of incident light, and having a reflectivity peak encompassing an emission wavelength of the light-emissive region.

30

27. A light-emissive device as claimed in claim 26, wherein the reflective structure is a distributed Bragg reflector.

35

28. A light-emissive device as claimed in claim 26 or 27, wherein the second electrode comprises a layer located on the non-viewing side of the reflective structure and a plurality of through paths passing through the reflective structure for electrical conduction between the said layer of the second electrode and the light-emissive region.

40

29. A light-emissive device as claimed in claim 28, wherein the through paths occupy less than 15% of the emissive area of the device.

45

30. A light-emissive device as claimed in any of claims 26 to 29, wherein the cathode comprises a transparent layer located between the reflective structure and the light-emissive region.

50

55

5

31. A light-emissive device as claimed in claim 30 as dependant on claim 28 or 29, wherein the transparent layer is in contact with the through paths.

10

32. A light-emissive device as claimed in any of claims 26 to 31, wherein the second electrode comprises an electrically conductive material.

15

33. A light-emissive device as claimed in any of claims 26 to 32, wherein the light-emissive layer comprises an organic light-emissive material.

20

34. A light-emissive device as claimed in any of claims 26 to 33, wherein the light-emissive layer comprises a polymer light-emissive material.

25

35. A light-emissive device as claimed in any of claims 26 to 34, wherein the light-emissive layer comprises a conjugated polymer material.

30

36. A light-emissive device substantially as herein described with reference to figures 2 to 8 of the accompanying drawings.

35

40

45

50

55

1/3




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5

3/3




Fig. 6




Fig. 7




Fig. 8

INTERNATIONAL SEARCH REPORT

Intern. Application No
PCT/GB 99/04050A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L51/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01L H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 05, 31 May 1996 (1996-05-31) - & JP 08 008065 A (TOPPAN PRINTING CO LTD), 12 January 1996 (1996-01-12) abstract column 4, line 14-41	1,2, 7-10,12, 13,36
X	EP 0 483 783 A (GOLD STAR CO) 6 May 1992 (1992-05-06) abstract column 3, line 12 -column 4, line 14; figures -/-	1-3,6, 10-12, 16,36

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

10 March 2000

Date of mailing of the international search report

21/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 6818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 51 651 epo nl,
Fax (+31-70) 340-3015

Authorized officer

De Laere, A

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/GB 99/04050

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DIRR S ET AL: "ORGANIC ELECTRO- AND PHOTOLUMINESCENT MICROCAVITY DEVICES" ADVANCED MATERIALS, DE, VCH VERLAGSGESELLSCHAFT, WEINHEIM, vol. 10, no. 2, 22 January 1998 (1998-01-22), pages 167-171, XP000727865 ISSN: 0935-9648 page 170, column 2, line 41 -page 171, column 1, line 52; figure 5	17-20, 22, 25, 36
X	EP 0 430 041 A (DAIDO STEEL CO LTD) 5 June 1991 (1991-06-05) abstract; claims; figures	26, 32
A	EP 0 838 976 A (TDK CORP) 29 April 1998 (1998-04-29) column 7, line 35-45	1-4, 6, 8, 10-13
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 12, 26 December 1996 (1996-12-26) -& JP 08 222374 A (IDEMITSU KOSAN CO LTD), 30 August 1996 (1996-08-30) abstract	1, 2, 6, 7, 10-13, 16
A	PATENT ABSTRACTS OF JAPAN vol. 018, no. 195 (E-1533), 5 April 1994 (1994-04-05) -& JP 06 005367 A (PIONEER ELECTRON CORP), 14 January 1994 (1994-01-14) abstract; figures	1-4, 6, 10-12
A	GYOUTOKU A ET AL: "Organic electroluminescent dot-matrix display using carbon underlayer" PROCEEDINGS OF THE 1997 INTERNATIONAL CONFERENCE ON ELECTROLUMINESCENCE OF MOLECULAR MATERIALS AND RELATED PHENOMENA; FUKUOKA, JPN MAY 21-24 1997, vol. 91, no. 1-3, 21 May 1997 (1997-05-21), pages 73-75, XP000890057 Synth Met; Synthetic Metals Dec 1997 Elsevier Science S.A., Lausanne, Switzerland the whole document	1
	-/-	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 99/04050

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JABBOUR G E ET AL: "ALUMINUM BASED CATHODE STRUCTURE FOR ENHANCED ELECTRON INJECTION INELECTROLUMINESCENT ORGANIC DEVICES" APPLIED PHYSICS LETTERS,US,AMERICAN INSTITUTE OF PHYSICS. NEW YORK, vol. 73, no. 9, 31 August 1998 (1998-08-31), pages 1185-1187, XP000781203 ISSN: 0003-6951 abstract	1,7-9
A	US 5 674 636 A (MILLER TIMOTHY MARK ET AL) 7 October 1997 (1997-10-07) column 6, line 21-43	17-22

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. nat. Application No

PCT/GB 99/04050

Patent document checked in search report	Publication date	Patent family member(s)	Publication date
JP 08008065 A	12-01-1996	NONE	
EP 0483783 A	06-05-1992	KR 9310129 B	14-10-1993
		DE 69122030 D	17-10-1996
		DE 69122030 T	06-02-1997
		JP 2117000 C	06-12-1996
		JP 4264390 A	21-09-1992
		JP 8024070 B	06-03-1996
		US 5352543 A	04-10-1994
EP 0430041 A	05-06-1991	JP 2720554 B	04-03-1998
		JP 3163882 A	15-07-1991
		JP 3163883 A	15-07-1991
		CA 2030368 A	23-05-1991
		DE 69025273 D	21-03-1996
		DE 69025273 T	11-07-1996
		US 5132750 A	21-07-1992
EP 0838976 A	29-04-1998	JP 10125469 A	15-05-1998
		US 5969474 A	19-10-1999
JP 08222374 A	30-08-1996	JP 2931229 B	09-08-1999
JP 06005367 A	14-01-1994	NONE	
US 5674636 A	07-10-1997	US 5478658 A	26-12-1995
		DE 69510863 D	26-08-1999
		DE 69510863 T	13-01-2000
		EP 0683623 A	22-11-1995
		JP 7320864 A	08-12-1995